# **IOP**science

Home Search Collections Journals About Contact us My IOPscience

Calculating line intensities of  ${}^{1}S_{0}$  emission through standard and modified Judd–Ofelt theories in  $Pr^{3+}$ -doped CaAl<sub>12</sub>O<sub>19</sub> and SrAl<sub>12</sub>O<sub>19</sub>

This article has been downloaded from IOPscience. Please scroll down to see the full text article. 2010 J. Phys.: Condens. Matter 22 155501 (http://iopscience.iop.org/0953-8984/22/15/155501)

View the table of contents for this issue, or go to the journal homepage for more

Download details: IP Address: 221.8.12.150 The article was downloaded on 10/09/2012 at 01:48

Please note that terms and conditions apply.

J. Phys.: Condens. Matter 22 (2010) 155501 (6pp)

## Calculating line intensities of <sup>1</sup>S<sub>0</sub> emission through standard and modified Judd–Ofelt theories in Pr<sup>3+</sup>-doped CaAl<sub>12</sub>O<sub>19</sub> and SrAl<sub>12</sub>O<sub>19</sub>

Jinsu Zhang<sup>1,2</sup>, Feng Liu<sup>3</sup>, Xiao-jun Wang<sup>1,4</sup> and Jiahua Zhang<sup>1,5</sup>

 <sup>1</sup> Key Laboratory of Excited State Processes, Changchun Institute of Optics, Fine Mechanics and Physics, Chinese Academy of Sciences, Changchun 130033, People's Republic of China
 <sup>2</sup> Graduate School of Chinese Academy of Sciences, Beijing 100039, People's Republic of China

<sup>3</sup> Department of Physics and Astronomy, University of Georgia, Athens, GA 30602, USA

<sup>4</sup> Department of Physics, Georgia Southern University, Statesboro, GA 30460, USA

E-mail: zhangjh@ciomp.ac.cn

Received 20 January 2010, in final form 7 March 2010 Published 26 March 2010 Online at stacks.iop.org/JPhysCM/22/155501

#### Abstract

A modified Judd–Ofelt theory is used in this paper to treat the electric dipole transitions within the 4f<sup>2</sup> configuration of  $Pr^{3+}$  by considering two main perturbing components of 4f5d and 4fn'g. Through the energy-level calculation and standard tensorial analysis, the explicit distance between the 4f5d configuration and the <sup>1</sup>S<sub>0</sub> state and other lower 4f<sup>2</sup> energy levels are determined. The rare-earth ion  $Pr^{3+}$  substituted at  $Sr^{2+}$  sites in  $SrAl_{12}O_{19}$  (SAO) and  $Ca^{2+}$  sites in  $CaAl_{12}O_{19}$  (CAO) has the site symmetry of  $D_{3h}$ . The standard Judd–Ofelt parameters  $A_{33}^2$ ,  $A_{33}^4, A_{53}^4, A_{53}^6, A_{73}^6$  are included in the calculation, together with odd- $\lambda$  parameters  $A_{33}^3$  and  $A_{53}^5$ . The emitting line intensities originating from <sup>1</sup>S<sub>0</sub> and <sup>3</sup>P<sub>0</sub> are then calculated. Compared with the experimental measurements, the modified model yields better results than the standard Judd–Ofelt theory.

#### 1. Introduction

The standard Judd–Ofelt theory [1, 2] provided a general and successful theoretical framework for calculating the electric dipole transitional intensities between the J multiplets of rare-earth ions. Three parameters  $\Omega_2$ ,  $\Omega_4$ , and  $\Omega_6$  were acquired by a fit to the experimental data. In the case of splitting of J induced by the crystal field, Axe [3] studied the transitional intensities between the crystal-field energy levels. Subsequently, a more general parameter set was proposed by Reid and Richardson,  $A_{tp}^{\lambda}$  [4], which incorporates more information on the structure and on the lanthanide– ligand interaction. The degeneracy of the opposite-parity configurations is assumed in the standard Judd–Ofelt theory. Meanwhile, a closure approximation that the opposite-parity configurations lie far above the 4f<sup>N</sup> configuration is applied in the theory. The closure approximation breaks down when applied to the  ${}^{1}S_{0}$  state of trivalent praseodymium, of which the  ${}^{1}S_{0}$  is near the 4f5d configuration. To solve the problem, modifications of the standard Judd–Ofelt theory have been introduced [5–8]. Because of the unknown energylevel structure of the opposite-parity configurations, the above modifications are based on the closure approximation. In order to verify the discrepancy of the closure approximation, knowledge of the opposite-parity configurations is desired.

Recently, there has been a growing interest in the study of the high energy spectroscopy of rare-earth ions as part of the effort to design new phosphors for lamps and displays. Dorenbos [9–11] has demonstrated the lowest  $4f^{N-1}5d$  state in hundreds of materials. Furthermore, Reid [12] has established a theoretical model to calculate the  $4f^{N-1}5d$  energy levels. The development of the above-mentioned has greatly aided the present work.

<sup>&</sup>lt;sup>5</sup> Author to whom any correspondence should be addressed.



Figure 1. X-ray powder diffraction patterns of (a)  $Ca_{0.99}Al_{12}O_{19}$ :0.01 $Pr^{3+}$  and (b)  $Sr_{0.99}Al_{12}O_{19}$ :0.01 $Pr^{3+}$ .

In this paper, the crystal-field parameters are obtained by fitting the experimental data using f shell programs which are based on the model of Reid. The  $4f^2$  and 4f5d energy levels of  $Pr^{3+}$  are calculated. The opposite-parity mixing states of the 4f5d with the  $4f^2$  transitional states are determined to give the energy difference between the 4f5d and  $4f^2$  states. The modified Judd–Ofelt theory is used to calculate the transitional intensities. According to this method, the total transitional intensities from the  ${}^1S_0$  and  ${}^3P_0$  levels to the lower *J* multiplets are calculated by summing over all the transitional intensities between crystal-field levels. Finally, the calculated results by the standard and modified Judd–Ofelt theories are listed and compared with the experimental data. The present method leads to an understanding of the limit of the existing of the standard Judd–Ofelt theory.

#### 2. Experimental details

The single-crystal powder Ce<sup>3+</sup> and Pr<sup>3+</sup> doped CAO and SAO samples were prepared by high temperature solid-state reaction. The raw materials CaCO<sub>3</sub>, SrCO<sub>3</sub>,  $\gamma$ -Al<sub>2</sub>O<sub>3</sub>, and Pr<sub>6</sub>O<sub>11</sub>, CeO<sub>2</sub> with a proper amount of CaF<sub>2</sub> and SrF<sub>2</sub> (5 mol at.%) added as a flux and Mg(OH)<sub>2</sub>·4MgCO<sub>3</sub>·6H<sub>2</sub>O acting as a charge compensator were weighed with a definite chemistry dosage. The mixtures were ground homogeneously for 1 h, preheated at 200 °C in air for a day, and then sintered at 1500 °C in a CO reducing atmosphere for 5 h.

The crystalline structure of the sample was investigated by x-ray diffraction (XRD) patterns with a Cu target radiation source, and a pure SAO or CAO phase was observed, as shown in figure 1. A pure single powder sample was synthesized. The SAO or CAO crystallizes in a face centered cubic structure belonging to the  $P6_3/mmc$  space group. The rare-earth dopants occupy  $Sr^{2+}$  or  $Ca^{2+}$  sites with the point group symmetry of  $D_{3h}$  [13]. The photoluminescence excitation (PLE) and diffuse reflection spectra of  $Ce^{3+}$  and the photoluminescence (PL) spectrum of  ${}^{1}S_{0}$  to the low lying energy levels of  $Pr^{3+}$  were measured using a HITACHI F-4500 fluorescence spectrophotometer. The PL spectrum of  ${}^{3}P_{0}$  to the low lying energy levels of  $Pr^{3+}$  was detected by a boxcar-162 integrator upon excitation by an optical parametric oscillator



**Figure 2.** Excitation and diffuse reflection spectra (inside) of (a)  $Ca_{0.99}Al_{12}O_{19}:0.01Ce^{3+}$  and (b)  $Sr_{0.99}Al_{12}O_{19}:0.01Ce^{3+}$  monitored at 324 nm and 307 nm, respectively.

(OPO). All of the spectra have been corrected by the response of the detector. The fluorescence lifetime of  ${}^{3}P_{0}$  was detected at a low temperature of 10 K.

#### 3. Result and discussion

#### 3.1. Energy-level calculation

The energy levels of the  $4f^2$  and 4f5d configurations are calculated by f shell programs. The free ions and crystalfield parameters for the  $4f^2$  configuration are taken from [14] and [15], respectively. The crystal-field parameters for 5d electrons are obtained by fitting the excitation spectra of  $Ce^{3+}$ doped CAO and SAO shown in figure 2. In this paper, we adopt antitheses to analyze the factors which affect the position of the 4f5d configuration of  $Pr^{3+}$  according the spectra of  $Ce^{3+}$ . The barycenter of the 4f5d configuration lies in the vacuum ultraviolet region, which will fall with increasing covalence. The splitting range of the 4f5d configuration depends on the crystal-field strength. Figure 2 shows the excitation and diffuse reflection spectra of the Ce3+ doped CAO and SAO systems. The diffuse reflection spectra of  $Ce^{3+}$  exhibits the lowest 5d configuration located at 37965 cm<sup>-1</sup> in CAO and 38 197 cm<sup>-1</sup> in SAO, indicating an energy difference of about  $232 \text{ cm}^{-1}$ . The onset absorption of the  $\text{Pr}^{3+}$  4f5d bands is at 212 nm (47 170 cm<sup>-1</sup>) and 211 nm (47 393 cm<sup>-1</sup>) in CAO and SAO, respectively [16]. The covalence of alkaline earth metal ion  $Ca^{2+}$  is stronger than  $Sr^{2+}$ , so the barycenter of the 5d configuration of  $Ce^{3+}$  in CAO is lower than that in SAO. Otherwise, the cation-anion distance in CAO (average Ca-O distance approximate 2.71 Å) [17] is shorter than that in SAO (average Sr-O distance approximate 2.83 Å) [18], enhancing the crystal-field strength in the CAO host. In other words, the 5d configuration splitting of  $Ce^{3+}$  in CAO is larger than that in SAO. From the excitation spectrum of  $Ce^{3+}$ , we find that the splitting range of the 5d configuration is about  $6878 \text{ cm}^{-1}$ in CAO and 6808  $cm^{-1}$  in SAO. The energy difference is only 70 cm<sup>-1</sup>, which is much smaller than 232 cm<sup>-1</sup>, the energy difference of the lowest 5d configuration. We can conclude from the above analysis that the barycenter shift will

have a relative large contribution to the position of the 5d configuration in Ce<sup>3+</sup>-doped CAO and SAO systems. Finally, the 5d crystal-field parameters  $B_{kq}$  (dd) are obtained by fitting the excitation spectra of Ce<sup>3+</sup> which give the 5d energy levels of Ce<sup>3+</sup>. The difference of the f–d barycenter  $\Delta_E$  (fd) is adjusted. Agreement between the experimental and calculation results has been achieved. Next, we obtain the values of the parameters:  $\Delta_E$  (fd) = 39 493 cm<sup>-1</sup>, 39 593 cm<sup>-1</sup> and  $B_{20}$ (dd) = 759 cm<sup>-1</sup>, 748 cm<sup>-1</sup> and  $B_{40}$ (dd) = 11 187 cm<sup>-1</sup>, 11 057 cm<sup>-1</sup> for Ce<sup>3+</sup> in CAO and SAO. The fitting results show a good agreement with the above analysis, furthermore the 4f5d energy levels of Pr<sup>3+</sup> are calculated.

#### 3.2. Calculation method and f-f intensity parameters

In rare-earth doped system, the intraconfigurational f–f electric dipole transitions can arise from the admixture of the 4f<sup>N</sup> transitional states with their opposite-parity configurations. These perturbing configurations have a higher energy than the 4f<sup>N</sup> configurations and are mostly of the type 4fn'd and 4fn'g [1]. The perturbing configuration of 4f5d for the type 4fn'd is considered. The configurations for  $n' \ge 6$  of the type 4fn'd can be neglected due to the much smaller quantity in the intensity calculation. All the configurations of the type 4fn'g should be considered for the admixture. The nonzero matrix elements of the electric dipole operator between the initial  $\langle \varphi_i |$  and final states  $|\varphi_f\rangle$  of the 4f<sup>N</sup> are

$$\langle 4\mathbf{f}^{N}\varphi_{\mathbf{i}}|\hat{D}_{p}^{1}|4\mathbf{f}^{N}\varphi_{\mathbf{f}}\rangle = \sum_{\varphi''} \left[ \frac{\langle \varphi_{\mathbf{i}}|\hat{D}_{p}^{1}|\varphi_{\mathbf{i}}''\rangle\langle \varphi_{\mathbf{i}}''|H_{\mathrm{CF}}|\varphi_{\mathbf{f}}\rangle}{E(\varphi_{\mathbf{f}}) - E(\varphi_{\mathbf{f}}'')} + \frac{\langle \varphi_{\mathbf{f}}|\hat{D}_{p}^{1}|\varphi_{\mathbf{f}}''\rangle\langle \varphi_{\mathbf{f}}''|H_{\mathrm{CF}}|\varphi_{\mathbf{i}}\rangle}{E(\varphi_{\mathbf{i}}) - E(\varphi_{\mathbf{i}}'')} \right]$$
(1)

where the corresponding Hamiltonian can be written as

$$H_{\rm CF}({\rm odd}) = \sum_{k,q,j} A_q^k \cdot r^k \hat{c}_q^k(j), \qquad k = {\rm odd \ number.} \quad (2)$$

The electric dipole operator  $\hat{D}_p^1$ , which dominates the relevant transition, is then expressed as

$$\hat{D}_{p}^{1} = \sum_{j} r \hat{c}_{p}^{1}(j).$$
(3)

In equation (1) the subscript *i* and *f* denote the initial or final mixing states, and  $\hat{c}_q^k$  is the irreducible tensor operator of rank *k*; the values of *q* are determined by site symmetry.

In this paper, we will focus on the two major transitions originating from the  ${}^{3}P_{0}$  and  ${}^{1}S_{0}$  initial states of  $Pr^{3+}$ . Two major opposite-parity configurations of 4f5d and 4fn'g have been considered in the admixture. The Judd–Ofelt theory gives an expression for the electric dipole transitional strengths between the initial state and final state

$$\langle i | D_p^{(1)} | f \rangle_g = \sum_{k,q,\lambda} A_{kq(g)}^{\lambda} [k]^{1/2} (-1)^{p+q+J-M} \\ \times \begin{pmatrix} 1 & \lambda & k \\ p & -p-q & q \end{pmatrix} \begin{pmatrix} J & \lambda & J' \\ -M & p+q & M' \end{pmatrix} \\ \times \langle \varphi J | | U^{(\lambda)} | | \varphi' J' \rangle$$

$$(4)$$

where

1

$$\begin{aligned} A^{A}_{kq(g)} &= -A_{kq} \Xi(k,\lambda)_{(g)} (2\lambda+1)/\sqrt{2k+1} \\ \Xi(k,\lambda)_{(g)} &= 14 \sum_{n'g} (2\times 4+1)(-1)^{4+3} \\ &\times \begin{cases} 1 & \lambda & k \\ 3 & 4 & 3 \end{cases} \begin{pmatrix} 3 & 1 & 4 \\ 0 & 0 & 0 \end{pmatrix} \begin{pmatrix} 4 & k & 3 \\ 0 & 0 & 0 \end{pmatrix} \frac{\langle r \rangle \langle r^k \rangle}{\Delta(n'g)} \end{aligned}$$

 $\langle r \rangle$  and  $\langle r^k \rangle$  in the above equation are the radial integrals between different configurations. The approximation  $\sum_{n'} \langle 4f | \hat{r} | n'g \rangle \langle 4f | \hat{r}^k | n'g \rangle = \langle 4f | \hat{r}^{k+1} | 4f \rangle$  can be applied to the 4fn'g configuration [19]. The energy denominator of the initial state  $E(\varphi_i) - E(\varphi_i'')$  and the final state  $E(\varphi_f) - E(\varphi_f'')$ are assumed equal, in other words it is assumed that the perturbing configurations lie far above the optical transitional states within the 4f shell. This assumption is suitable for the 4fn'g configuration due to the large energy difference from the 4f<sup>2</sup> configuration. Nevertheless, the 4f5d configuration is near above the 4f<sup>2</sup> transitional states, especially for the <sup>1</sup>S<sub>0</sub> state, the energy levels of 4f<sup>2</sup> and 4f5d are calculated, and the main 4f5d components mixed into the 4f<sup>2</sup> initial and final states will be determined.

The f-d mixing is determined by calculating the matrix elements of the irreducible tensor operator about the electric dipole transitions  $\langle \varphi_i | \hat{D}_p^1 | \varphi_i'' \rangle$  and  $\langle \varphi_f | \hat{D}_p^1 | \varphi_f'' \rangle$  and odd-rank crystal fields  $\langle \varphi_i'' | H_{CF} | \varphi_f \rangle$  and  $\langle \varphi_f'' | H_{CF} | \varphi_i \rangle$  between the states of 4f<sup>2</sup> and 4f5d. In Pr<sup>3+</sup> doped SAO, a detailed analysis is reported in [20] to give the opposite-parity mixing states with the <sup>3</sup>P<sub>0</sub> and <sup>1</sup>S<sub>0</sub> initial or final transition states in D<sub>3h</sub> symmetry, which will be used to confirm the values of the energy denominators  $E(\varphi_f) - E(\varphi_f'')$  and  $E(\varphi_i) - E(\varphi_i'')$  in our calculation. An analogous calculation will be done in the Pr<sup>3+</sup> doped CAO, and the corresponding opposite-parity mixing states and their values are listed in table 1.

The  ${}^{1}S_{0}$  of  $Pr^{3+}$  lies so near the 4f5d configuration that discrepancies are observed when the Judd–Ofelt theory is applied to treat the intensity calculation for the  ${}^{1}S_{0}$  state. Here, we consider the difference of energy denominators in the initial and final transitional states and give a modified expression

$$\langle i | \hat{D}_{p}^{(1)} | f \rangle_{d} = \sum_{k,q,\lambda} A_{kq(d)}^{\lambda} [k]^{1/2} (-1)^{p+q+J-M} \\ \times \left( \frac{1}{E(\varphi_{f}) - E(\varphi_{f}'')} + \frac{(-1)^{1+\lambda+k}}{E(\varphi_{i}) - E(\varphi_{i}'')} \right) \\ \times \left( \frac{1}{p} - p - q - q \right) \left( \begin{array}{c} J & \lambda & J' \\ -M & p + q & M' \end{array} \right) \\ \times \langle \varphi J || U^{(\lambda)} || \varphi' J' \rangle$$
(5)

where

$$\begin{aligned} A_{kq(d)}^{\lambda} &= -A_{kq} \Xi(k,\lambda)_{(d)} (2\lambda+1)/\sqrt{2k+1} \\ \Xi(k,\lambda)_{(d)} &= 7 \sum_{5d} (2\times 2+1)(-1)^{2+3} \\ &\times \begin{cases} 1 & \lambda & k \\ 3 & 2 & 3 \end{cases} \begin{pmatrix} 3 & 1 & 2 \\ 0 & 0 & 0 \end{pmatrix} \begin{pmatrix} 2 & k & 3 \\ 0 & 0 & 0 \end{pmatrix} \langle r \rangle \langle r^k \rangle. \end{aligned}$$

The reduced matrix element  $\langle \varphi J || U^{(\lambda)} || \varphi' J' \rangle$  can be calculated using the doubly reduced matrix elements  $\langle f^N \gamma SL || U^{(\lambda)} || f^N \gamma' S' L' \rangle$  which are tabulated by Nielson and Koster [21]. The

Table 1. The opposite-parity mixing states of the 4f5d with  ${}^{1}S_{0}$  and  ${}^{3}P_{0}$  states in  $Pr^{3+}$  doped CAO and SAO and their energy values.

	4f5d configuration						
4f2 configuration		Energy denominators			Energy denominators		
Initial states 4f2 <i>SLJM</i>	Mixing with initial states 4f5dS"L"J"M"	CAO	SAO	Mixing with final states 4f5dS"L"J"M"	CAO	SAO	
${}^{1}S_{0(0)}$	${}^{1}F_{3(-3,+3)}$ ${}^{1}H_{5(-3,+3)}$	64 062 72 244	63 934 72 221	${}^{3}P_{1(\pm 1)}$ ${}^{1}P_{1(0)}$	61 687 72 556	61 660 72 518	
<sup>3</sup> P <sub>0(0)</sub>	${}^{3}D_{3(-3,+3)}$ ${}^{3}G_{3(-3,+3)}$ ${}^{3}G_{5(-3,+3)}$	62 615 58 520 63 145	62 585 58 103 63 100	${}^{3}D_{1(\pm 1)}$ ${}^{3}D_{1(0)}$	61 663 61 801	61 629 61 779	

matrix element includes both even and odd terms.  $\Xi(k, \lambda)_{(g)}$ in equation (4) contains the information about the average difference between the 4f<sup>2</sup> and 4fn'g configurations.  $\Xi(k, \lambda)_{(g)}$ is considered as an unknown quantity in standard Judd–Ofelt theory, while in the calculation for dealing with the mixing of the 4f5d configuration, the energy denominators are known quantitatively and appear in the transitional expression. The  $(\cdots)$  and  $\{\cdots\}$  in equations are the 3 - j and 6 - j symbols, respectively, and [k] equals to 2k + 1. The Judd–Ofelt theory considers the same energy denominators, so the nonzero condition of equation (4) requires even- $\lambda$  because the exponent  $1 + \lambda + k$  should be even and k is odd in equation (2), whereas both even and odd  $\lambda$  are included in equation (5) because of the difference of the energy denominators.

The electric dipole and strengths between an initial state  $\varphi J$  and a final state  $\varphi' J'$  in Judd–Ofelt theory is written as

$$S^{\text{ED}}(\varphi J, \varphi' J') = e^2 \sum_{i,f} |\langle i | \hat{D}_p^{(1)} | f \rangle_g + \langle i | \hat{D}_p^{(1)} | f \rangle_d |^2.$$
(6)

The radiative decay rates for electric dipole transitions is expressed as

$$A(\varphi J, \varphi' J') = \frac{64\pi^4 \sigma^3}{3h(2J+1)} \chi^{\text{ED}} S^{\text{ED}}(\varphi J, \varphi' J'), \quad (7)$$

where  $\chi^{\text{ED}} = \frac{n(n^2+2)^2}{9}$  is the Lorentz local field correction factor for the electric dipole emission. We have approximated the index versus wavelength in SAO and CAO by  $n_{(\lambda)} =$  $1.75 + (12700 \text{ nm}^2)/\lambda^2$ , obtained according to the closely related crystal LaMgAl<sub>11</sub>O<sub>19</sub> [22], because all three of them have almost the same hexagonal magnetoplumbite structure. *e* is the elementary charge; *h* is Planck's constant; and  $\sigma$  is the wavenumber at the emission maximum.

In the present  $D_{3h}$  site symmetry, the necessary phenomenological intensity parameters are determined by equations (4) and (5) and a set of intensity parameters  $A_{33(g)}^2$ ,  $A_{33(g)}^4$ ,  $A_{53(g)}^4$ ,  $A_{53(g)}^6$  and  $A_{73(g)}^6$ , together with  $A_{33(d)}^2$ ,  $A_{33(d)}^3$ ,  $A_{43(d)}^4$ ,  $A_{53(d)}^4$ ,  $A_{53(d)}^5$  and  $A_{53(d)}^6$ , are included. The relationships between these parameters are calculated using equations (4) and (5):

$$\frac{A_{33(d)}^3}{A_{33(d)}^2} = -2.4749 \qquad \frac{A_{33(d)}^4}{A_{33(d)}^2} = 3.5178$$
$$\frac{A_{53(d)}^5}{A_{53(d)}^4} = -3.6667 \qquad \frac{A_{53(d)}^6}{A_{53(d)}^4} = 9.6896$$



**Figure 3.** Emission spectra of (a)  $Ca_{0.99}Al_{12}O_{19}:0.01Pr^{3+}$  and (b)  $Sr_{0.99}Al_{12}O_{19}:0.01Pr^{3+}$  upon  ${}^{3}H_{4} \rightarrow {}^{1}P_{0}$  excitation (466 nm). (This figure is in colour only in the electronic version)

$$\frac{A_{33(g)}^4}{A_{33(g)}^2} = 0.3838 \qquad \frac{A_{53(g)}^6}{A_{53(g)}^4} = 0.1242.$$

Thus, only five parameters  $A_{33(d)}^2$ ,  $A_{53(d)}^4$ ,  $A_{33(g)}^2$ ,  $A_{53(g)}^4$ and  $A_{73(g)}^6$  in the intensity calculation perform an important function. The intensity parameters  $A_{kq}^{\lambda}$  contain the unknown quantities of the odd-rank crystal-field coefficients  $A_{kq}$  and the interconfigurational radial integral  $\langle r \rangle$  and  $\langle r^k \rangle$ . Their values are usually calculated according to the Hartree–Fock method [23, 24]. In this work, the initial values of intensity parameters are determined according to the values of  $A_{kq}$  in [1] and the values of  $\langle r \rangle$  and  $\langle r^k \rangle$  in [25]. The final given values are obtained by fitting the measured data through the least-squares deviation [26].

### *3.3. Intensity calculation and comparison with Judd–Ofelt theory*

In the  $Pr^{3+}$  doped SAO and CAO system, the intensity parameters  $A_{33(d)}^2$ ,  $A_{53(d)}^4$ ,  $A_{33(g)}^2$ ,  $A_{53(g)}^4$  and  $A_{73(g)}^6$  are determined by fitting the relative transitional intensities originating from the <sup>3</sup>P<sub>0</sub> level to the lower lying *SLJ* multiplets. The experimental data are shown in table 2. which are obtained by integrating the emission spectrum shown in figure 3. The calculated intensity ratios for the transition to the *SLJ* states are obtained through summing over all the electric dipole

Table 2. Experimental and calculated transition strengths from  ${}^{3}P_{0}$  in  $Pr^{3+}$ -doped CAO and SAO.

Final states $ f^{N}[SL]J\rangle$	Energy difference (cm <sup>-1</sup> )	CAO			SAO		
		This work	Judd-Ofelt	Measured	This work	Judd–Ofelt <sup>a</sup>	Measured <sup>a</sup>
$^{3}H_{4}$	20654	1.000	1.000	1.000	1.000	1.000	1.000
$^{3}H_{5}$	18 568	0.004	0.000	0.082	0.004	0.000	0.086
$^{3}H_{6}$	16396	0.072	0.432	0.204	0.085	0.457	0.183
${}^{3}F_{2}$	15759	0.119	0.000	0.121	0.119	0.000	0.117
${}^{3}F_{4}$	13 935	0.246	0.213	0.065	0.246	0.213	0.063
Lifetime		$30 \ \mu s$	30 µs	30 µs [ <b>25</b> ]	36 µs	36 µs	36 μs [ <mark>10</mark> ]

<sup>a</sup> Taken from the data in [10].

**Table 3.** Experimental and calculated transition strengths from  ${}^{1}S_{0}$  in  $Pr^{3+}$ -doped CAO and SAO.

Final states $ f^{N}[SL]J\rangle$	Energy difference		CAO		SAO		
	$(cm^{-1})$	This work	Judd-Ofelt	Measured	This work	Judd–Ofelt <sup>a</sup>	Measured <sup>a</sup>
$^{3}H_{4}$	46 699	0.126	0.049	0.195	0.126	0.049	0.125
${}^{3}F_{4}$	39 981	0.68	0.326	0.519	0.680	0.326	0.549
${}^{1}G_{4}$	36967	1.000	1.000	1.000	1.000	1.000	1.000
${}^{1}D_{2}$	29 886	0.102	0.000	0.089	0.101	0.000	0.067
${}^{1}I_{6}$	25 400	0.196	0.857	0.484	0.231	0.907	0.344
Lifetime		482 ns	2160 ns	650 ns [25]	569 ns	2600 ns	678 ns [ <mark>10</mark> ]

<sup>a</sup> Taken from the data in [10].

intensities between crystal-field levels with the SLJ multiplets. The ratio of the intensity parameters will be determined by a least-square fitting between the measured and calculated data. Furthermore, in order to determine the absolute magnitude of the fitted variants, the natural lifetime of  ${}^{3}P_{0}$  is needed. In the condition of low Pr<sup>3+</sup> concentrations and low temperatures, the cross-relaxation and nonradiative processes of  ${}^{3}P_{0}$  can be ignored, thus the measured lifetime is considered as the inverse of all the probabilities of the radiative transitions in equation (7). Then the intensity parameters are listed as follows:

$$\begin{split} A^2_{33(d)} &= -30.67 \times 10^{-7}, \qquad A^4_{53(d)} = 7.43 \times 10^{-7}, \\ A^2_{33(g)} &= -0.0063 \times 10^{-12} \text{ cm}, \qquad A^4_{53(g)} = 0.0071 \times 10^{-12} \text{ cm} \\ \text{ and } \qquad A^6_{73(g)} &= -0.1104 \times 10^{-12} \text{ cm} \\ \text{ for } \text{Pr}^{3+} \text{ in CAO} \\ A^2_{33(d)} &= -27.90 \times 10^{-7}, \qquad A^4_{53(d)} = 6.85 \times 10^{-7}, \\ A^2_{33(g)} &= -0.0057 \times 10^{-12} \text{ cm}, \qquad A^4_{53(g)} = 0.00645 \times 10^{-12} \text{ cm} \\ \text{ and } \qquad A^6_{73(g)} &= -0.1040 \times 10^{-12} \text{ cm} \\ \text{ for } \text{Pr}^{3+} \text{ in SAO}. \end{split}$$

The given intensity parameters have a good interpretation for the  ${}^{3}P_{0}$  emission spectra. The calculated data from the present work and those from the standard Judd-Ofelt treatments, along with the experimental data are all listed in table 2. It can be noted that the hypersensitive transition of  ${}^{3}P_{0} \rightarrow {}^{3}F_{2}$  has been described well with experimental measurements. It is also worth noting that the transition of  ${}^{3}P_{0} \rightarrow {}^{3}H_{5}$  is forbidden in the standard Judd–Ofelt theory, but it is allowed in the present work. By comparing the data listed in table 2, we can see that the present calculated method shows a good agreement with the measurements.



Figure 4. Emission spectra of (a)  $Ca_{0.99}Al_{12}O_{19}:0.01Pr^{3+}$  and (b)  $Sr_{0.99}Al_{12}O_{19}:0.01Pr^{3+}$  upon  ${}^{3}H_{4} \rightarrow {}^{1}S_{0}$  excitation (198 nm).

The emitting intensities originating from higher energy level  ${}^{1}S_{0}$  are obtained, as listed in table 3. The experimental data are obtained by integrating the emission spectrum shown in figure 4. Due to the proximity of the 4f5d configuration, the modified model yields better results than the standard Judd-Ofelt theory. In order to make this more obvious further work will be done. A computer program for the theoretical spectrum will be completed.

#### 4. Conclusions

The crystal-field parameters for 5d electrons in CAO and SAO single powders are fitted to the  $Ce^{3+}$  spectra. Next, the accurate energy-level schematics of the  $4f^2$  and 4f5dconfigurations in Pr3+ doped CAO and SAO systems are calculated. Furthermore, a theoretical method for calculating the electric dipole transitional intensities within the 4f<sup>2</sup>

configuration in  $Pr^{3+}$  doped CAO and SAO systems has been proposed. Two major opposite-parity configurations of 4f5d and 4fn'g have been considered for the parity-state mixing. The explicit mixing 4f5d compositions have been given. The values of intensity parameters are determined by the leastsquares fitting between the experimental and calculated data. The present calculated method gives better results than the standard Judd–Ofelt treatments for the optical transition of the  ${}^{1}S_{0}$  and  ${}^{3}P_{0}$  energy levels.

#### Acknowledgments

This work is financially supported by the National Nature Science Foundation of China (10834006, 10774141, 10904141, 10904140), the MOST of China (2006CB601104), the Scientific project of Jilin province (20090134, 20090524) and the CAS Innovation Program.

#### References

- [1] Judd B R 1962 Phys. Rev. 127 750
- [2] Ofelt G S 1962 J. Chem. Phys. 37 511
- [3] Axe J D 1963 J. Chem. Phys. 39 1154
- [4] Reid M F and Richardson F S 1983 J. Chem. Phys. 79 5735
- [5] Levey C G 1990 J. Lumin. 45 168
- [6] Quimby R S and Miniscalco W J 1994 J. Appl. Phys. 75 613
- [7] Merkle L D, Zandi B, Moncorge R, Guyot Y, Verdun H R and McIntosh B 1996 J. Appl. Phys. 79 1849
- [8] Goldner P and Auzel F 1996 J. Appl. Phys. 79 7972

- [9] Dorenbos P 2000 J. Lumin. 91 91
- [10] Dorenbos P 2000 Phys. Rev. B 62 15640
- [11] Dorenbos P 2000 *Phys. Rev.* B **62** 15650
- [12] Reid M F, van Pieterson L, Wegh R T and Meijerink A 2000 Phys. Rev. B 62 14744
- [13] Merkle L D, Zandi B, Moncorge R, Guyot Y, Verdun H R and McIntosh B 1996 J. Appl. Phys. 79 1849
- [14] van Pieterson L, Reid M F, Wegh R T, Soverna S and Meijerink A 2002 Phys. Rev. B 65 045113
- [15] Zandi B, Merkle L D, Gruber J B, Wortman D E and Morrison C A 1997 J. Appl. Phys. 81 1047
- [16] Nie Z, Zhang J, Zhang X, Ren X, Di W, Zhang G, Zhang D and Wang X-J 2007 J. Phys.: Condens. Matter 19 076204
- [17] Utsunomiya A, Tanaka K, Morikawa H and Marumo F 1988 J. Solid State Chem. 75 197
- [18] Kimura K, Ohgaki M, Tanaka K, Morikawa H and Marumo F 1990 J. Solid State Chem. 87 186
- [19] Görller-Walrand C and Binnemans K 1998 Handbook on the Physics and Chemistry of Rare Earths vol 25, ed K A Gschneidner Jr and L Eyring (Amsterdam: North-Holland) p 140
- [20] Liu F, Zhang J, Lu S, Liu S, Huang S and Wang X-J 2006 Phys. Rev. B 74 115112
- [21] Nielson C W and Koster G F 1963 Spectroscopic Coefficients for the p<sup>n</sup>, d<sup>n</sup>, and f<sup>n</sup> Configurations (Cambridge: MIT Press)
- [22] Bykovskii P I, Lebedev V A, Pisarenko V F and Popov V V 1986 J. Appl. Spectrosc. 44 425
- [23] Morrison C A and Leavitt R P 1979 *J. Chem. Phys.* 71 2366
  [24] Esterowitz L, Bartoli F J, Allen R E, Wortman D E,
- Morrison C A and Leavitt R P 1979 *Phys. Rev.* B **19** 6442
- [25] Reid M F, van Pieterson L and Meijerink A 2002 J. Alloys Compounds 344 240
- [26] Porcher P and Caro P 1978 J. Chem. Phys. 68 4176